

Casting Gypsum Powder Specifications:

Results

Calcium Sulfate Percent	:	More than 95 %
Hydration to small knife / initial time	:	6-8.83 Minutes
Setting time	:	12-15 Minutes
Mesh	:	200 Micron
Remainder on the mesh number 80 sieve / 200 Micron	:	0 %
Durability compressive	:	10-12 Mpa
Tensile Strength	:	4-4.5 Mpa

