

Date:
No:
Appendix:

SAMAN SEPID
MINING COOPERATIVE CO.



Regular Natural Gypsum Rock Specifications Analyzed By Geochem Inspection Company.

TEST	METHOD	UNIT	RESULT
Purity	ASTM C471 M	% WT	92.13
Combined Water	ASTM C471 M	% WT	19.28
SiO ₂	ASTM C471 M	% WT	0.97
SO ₃	ASTM C471 M	% WT	42.84
Ca O	ASTM C471 M	% WT	30.01
Mg O	ASTM C471 M	% WT	0.65
R ₂ O ₃ (Iron & Aluminum oxide)	ASTM C471 M	% WT	0.69
Chloride	ASTM C471 M	% WT	0.007
Moisture	ASTM C471 M	% WT	0.63
Size			
0-50 mm	-	%	100

Add: 5TH Km of Khamir –Bandar Abbas Main Road, Khamir No:1 Gypsum Mine

E-mail:Khamirgypsum@gmail.com